

CATAS S.p.A. via Antica, 24/3 33048 San Giovanni al Natisone (UD) +39 0432 747211 - lab@catas.com www.catas.com Testing site: via Antica, 24/3 33048 San Giovanni al Natisone (UD) tel. +39 0432 747211 lab@catas.com

TEST REPORT

250725 / 1

 Date received:
 07/05/18

 Date of test:
 07/05/18

 Date of issue:
 11/06/18

Sample name:

11/06/18 Rif. 8 ALFAPANEL sp. 6,5 mm finitura ALFA (2 latl)

COSMO TECNOLOGY S.R.L. VIA ANTONIO DURANTE, 42 33080 PRATA DI PORDENONE (PN) ITALIA

Temperature and humidity cycles - UNI EN ISO 9142:2004

Type of cycle: D3

Test procedure:

The test has been carried out putting the sample in a forced ventilation climatic chamber, at the following conditions:

- 15 hours at 40 \pm 2 °C temperature and 90 \pm 3% r. h
- temperature is lowered to -20±2 °C in 60 minutes and then hold for 2 hours
- temperature is raised at 70 \pm 2 °C and 50 \pm 5 % r. h. in 60 minutes and then hold for 4 hours
- temperature is lowered to 40±2 °C in 60 minutes

Test results:

N° cycles	Remarks
21	At the end of testing no defects have been found.

This document is validated by digital signature and time stamping in accordance with the Italian laws and the European Directives which regulate the electronic signature systems.

Managing Director Dr. Andrea Giavon



CATAS S.p.A. via Antica, 24/3 33048 San Giovanni al Natisone (UD) +39 0432 747211 - lab@catas.com www.catas.com Testing site: via Antica, 24/3 33048 San Giovanni al Natisone (UD) tel. +39 0432 747211 lab@catas.com

TEST REPORT

250724 / 1

 Date received:
 07/05/18

 Date of test:
 07/05/18

 Date of issue:
 11/06/18

Sample name: Rif. 7 ALFAPANEL sp. 14 mm finitura ALFA (1 lato)

COSMO TECNOLOGY S.R.L. VIA ANTONIO DURANTE, 42 33080 PRATA DI PORDENONE (PN) ITALIA

Temperature and humidity cycles - UNI EN ISO 9142:2004

Type of cycle: D3

Test procedure:

The test has been carried out putting the sample in a forced ventilation climatic chamber, at the following conditions:

- 15 hours at 40 \pm 2 °C temperature and 90 \pm 3% r. h
- temperature is lowered to -20±2 °C in 60 minutes and then hold for 2 hours
- temperature is raised at 70 ± 2 °C and 50 ± 5 % r. h. in 60 minutes and then hold for 4 hours
- temperature is lowered to 40±2 °C in 60 minutes

Test results:

N° cycles	Remarks
21	At the end of testing no defects have been found.

This document is validated by digital signature and time stamping in accordance with the Italian laws and the European Directives which regulate the electronic signature systems.

Managing Director Dr. Andrea Giavon