

TEST REPORT

250721 / 1

Date received: 07/05/18  
Date of test: 07/05/18  
Date of issue: 11/06/18

COSMO TECHNOLOGY S.R.L.  
VIA ANTONIO DURANTE, 42  
33080 PRATA DI PORDENONE (PN)  
ITALIA

Sample name: Rif. 4 COSMOLIGHT sp. 10 mm HPL 0,9 mm (1 lato)

**Temperature and humidity cycles - UNI EN ISO 9142:2004**

Type of cycle: D3

Test procedure:

The test has been carried out putting the sample in a forced ventilation climatic chamber, at the following conditions:

- 15 hours at  $40 \pm 2$  °C temperature and  $90 \pm 3\%$  r. h
- temperature is lowered to  $-20 \pm 2$  °C in 60 minutes and then hold for 2 hours
- temperature is raised at  $70 \pm 2$  °C and  $50 \pm 5$  % r. h. in 60 minutes and then hold for 4 hours
- temperature is lowered to  $40 \pm 2$  °C in 60 minutes

Test results:

N° cycles	Remarks
21	At the end of testing no defects have been found.

*This document is validated by digital signature and time stamping in accordance with the Italian laws and the European Directives which regulate the electronic signature systems.*

  
Managing Director  
Dr. Andrea Glavon