

TEST REPORT

250728 / 1

Date received: 07/05/18
Date of test: 07/05/18
Date of issue: 11/06/18

COSMO TECHNOLOGY S.R.L.
VIA ANTONIO DURANTE, 42
33080 PRATA DI PORDENONE (PN)
ITALIA

Sample name: Rif. 11 COSMOTECH sp. 6,5 mm finitura HPL 0,9 mm (1 lato)

Temperature and humidity cycles - UNI EN ISO 9142:2004

Type of cycle: D3

Test procedure:

The test has been carried out putting the sample in a forced ventilation climatic chamber, at the following conditions:

- 15 hours at 40 ± 2 °C temperature and $90 \pm 3\%$ r. h
- temperature is lowered to -20 ± 2 °C in 60 minutes and then hold for 2 hours
- temperature is raised at 70 ± 2 °C and 50 ± 5 % r. h. in 60 minutes and then hold for 4 hours
- temperature is lowered to 40 ± 2 °C in 60 minutes

Test results:

N° cycles	Remarks
21	At the end of testing no defects have been found.

This document is validated by digital signature and time stamping in accordance with the Italian laws and the European Directives which regulate the electronic signature systems.

Managing Director
Dr. Andrea Giavon

TEST REPORT

250723 / 1

Date received: 07/05/18
Date of test: 07/05/18
Date of issue: 11/06/18

COSMO TECHNOLOGY S.R.L.
VIA ANTONIO DURANTE, 42
33080 PRATA DI PORDENONE (PN)
ITALIA

Sample name: Rif. 6 COSMOTECH sp. 10 mm finitura ALFA (1 lato)

Temperature and humidity cycles - UNI EN ISO 9142:2004

Type of cycle: D3

Test procedure:


The test has been carried out putting the sample in a forced ventilation climatic chamber, at the following conditions:

- 15 hours at 40 ± 2 °C temperature and $90 \pm 3\%$ r. h
- temperature is lowered to -20 ± 2 °C in 60 minutes and then hold for 2 hours
- temperature is raised at 70 ± 2 °C and 50 ± 5 % r. h. in 60 minutes and then hold for 4 hours
- temperature is lowered to 40 ± 2 °C in 60 minutes

Test results:

N° cycles	Remarks
21	At the end of testing no defects have been found.

This document is validated by digital signature and time stamping in accordance with the Italian laws and the European Directives which regulate the electronic signature systems.


Managing Director
Dr. Andrea Giavon

TEST REPORT

250726 / 1

Date received: 07/05/18
Date of test: 07/05/18
Date of issue: 11/06/18

COSMO TECHNOLOGY S.R.L.
VIA ANTONIO DURANTE, 42
33080 PRATA DI PORDENONE (PN)
ITALIA

Sample name: Rif. 9 COSMOTECH sp. 14 mm finitura VINILICO (1 lato)

Temperature and humidity cycles - UNI EN ISO 9142:2004

Type of cycle: D3

Test procedure:


The test has been carried out putting the sample in a forced ventilation climatic chamber, at the following conditions:

- 15 hours at 40 ± 2 °C temperature and $90 \pm 3\%$ r. h
- temperature is lowered to -20 ± 2 °C in 60 minutes and then hold for 2 hours
- temperature is raised at 70 ± 2 °C and 50 ± 5 % r. h. in 60 minutes and then hold for 4 hours
- temperature is lowered to 40 ± 2 °C in 60 minutes

Test results:

N° cycles	Remarks
21	At the end of testing no defects have been found.

This document is validated by digital signature and time stamping in accordance with the Italian laws and the European Directives which regulate the electronic signature systems.


Managing Director
Dr. Andrea Giavon